

A1
C10
Sub
D1

2. (Amended) The transparent substrate of claim 1, wherein the refractive index of the high-index multilayer comprising at least one titanium oxide layer is between 2.25 and 2.38.

A2

11. (Amended) The transparent substrate of claim 1, wherein the at least one additional high index layer has a refractive index of between 1.9 and 2.2 and comprises tantalum oxide, zirconium oxide, tin oxide, indium oxide, zinc oxide, silicon nitride, or aluminum nitride.

12. (Amended) The transparent substrate of claim 1, wherein the high-index multilayer comprises two contiguous layers and the additional high index layer is closer to the substrate than the titanium oxide layer.

A3
Sub B2

14. (Amended) The transparent substrate of claim 1, wherein the low index thin layers have a refractive index between 1.30 and 1.65 and comprise one or more of silicon oxide, aluminum oxide, aluminum oxyfluoride, aluminum fluoride, and magnesium fluoride, wherein the oxides are optionally halogenated.

A8
Sub
D1

20. (Amended) A glazing comprising the transparent substrate of claim 1.

A5

25. (Amended) The glazing of claim 21, for use as the internal or external glazing for buildings, to protect paintings, a motor-vehicle window, a mirror, a display screen, a decorative glass, a shop window, a shop-counter, or a refrigerated display-cabinet.

For the Examiner's convenience a complete list of the currently pending claims is attached hereto as Appendix B.